



# Industrial Research Services

Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

**Registered Testing Authority - CSIRO**

20 January 2011

Our Ref. EN13 / 420.2 03/0212

## TEST REPORT No. 5652.2s

Requested by: Kenbrock Flooring Pty Ltd  
63 Waterview Close  
Dandenong South  
VIC 3175

on (date): 14 January 2011

Manufacturer: Kenbrock Flooring Pty Ltd

Product Desc.: Kenflex, M2, Hammered Rubber tiles with Chip Inlay  
610x610mm

Sampling details:

Where: Delivered

Date: 14 January 2011

By whom: Courier

How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 3 pages

### SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

AS/NZS 4586:2004	Slip resistance classification of new pedestrian surface materials, Appendix D: OIL-WET Ramp	Result	Class
	Mean overall acceptance angle:	10.8°	R 10 [LOW*]

\* = CSIRO classification

In order to interpret the classifications, please refer to Standards Australia Handbook 197, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



# Industrial Research Services

Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

REPORT NO: 5652.2s  
ISSUE DATE: 20 January 2011  
MANUFACTURER: Kenbrock Flooring Pty Ltd  
PRODUCT DESC: Kenflex, M2, Hammered Rubber tiles with Chip Inlay  
610x610mm

Page 2 of 3

## SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

### OIL-WET RAMP TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH  
AS/NZS 4586:2004 (Appendix D)

Test Date: 19 January 2011

Location: Slip Resistance Laboratory

Sample Fixed

Joint width: 0 mm

Surface structure:  Smooth  
 Profiled  
 Structured

### RESULTS

Mean overall acceptance angle: 10.8 °

Displacement space: not tested

### CLASSIFICATION:

Slip Resistance Assessment Group:

R 10 [LOW\*]

Displacement Space Assessment Group:

\* = CSIRO classification



# Industrial Research Services


Materials Science & Engineering, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

REPORT NO: 5652.2s  
ISSUE DATE: 20 January 2011  
MANUFACTURER: Kenbrock Flooring Pty Ltd  
TILE DESC: Kenflex, M2, Hammered Rubber tiles with Chip Inlay  
610x610mm

Page 3 of 3

Date and Place 20 January 2011, Highett, Vic

Name, Title and Digital Signature:



**PETER WESTGATE**  
Project Leader  
Tel: 61 3 92526108  
Fax: 61 3 92526244  
Email: Peter.Westgate@csiro.au

**\*CSIRO recommended classification of Slip Resistance as determined from:  
AS/NZS 4586: 2004 Slip Resistance Classification of New Pedestrian Surface Materials (Appendices A & D).**

Wet Pendulum Class	BPN 4S Rubber	CSIRO Class LOW	CSIRO Class MEDIUM	CSIRO Class HIGH
V	>54	54-57	58-61	>61
W	45-54	45-48	49-51	52-54
X	35-44	35-38	39-41	42-44
Y	25-34	25-28	29-31	32-34
Z	<25	<18	18-21	22-25
Oil Wet Ramp Class	Angle (degrees)	CSIRO Class LOW	CSIRO Class MEDIUM	CSIRO Class HIGH
R9	≥6 to <10	≥6 to 7.5	7.6 to 9	9.1 to 9.9
R10	≥10 to <19	≥10 to 12	12.1 to 15	15.1 to 18.9
R11	≥19 to <27	≥19 to 21	21.1 to 24	24.1 to 26.9
R12	≥27 to <35	≥27 to 29	29.1 to 32	32.1 to 34.9
R13	≥35	≥35 to 36	36.1 to 38	≥38.1

This table should not be read or relied upon without reference to the CSIRO/Standards Australia publication:  
AS/NZS 4586 Slip Resistance Classification of New Pedestrian Surface Materials (Appendices A & D).

CSIRO has categorized the AS4586 classifications into sub-groups Low, Medium & High. The slip resistance test classification is still determined according to AS 4586 Australian Standard (Appendices A & D). The added information of Low, Medium and High allows professionals to make a better judgement of pedestrian floor requirements.