



Infrastructure Technologies

Gate 5, 2 Normanby Road Clayton VIC 3168, Australia

Telephone: 61 3 9545 2777 Web: <http://www.csiro.au>

Registered Testing Authority - CSIRO

19 June 2018

Our Ref. EN13 / 2556 03/0212

TEST REPORT No. 8103.1

Requested by: Kenbrock Pty Ltd
22-24 Edson Road
Dandenong South
Vic 3175

on (date): 4 May 2018

Manufacturer: Kenbrock

Product Desc.: Cushion Stone, Vinyl Tiles, PU Top Coat

Sampling details:

Where: At customer premises

Date: 7 May 2018

By whom: customer (delivered by courier)

How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 5 pages

SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

		Result	Class
AS 4586:2013	Slip resistance classification of new pedestrian surface materials Appendix A: WET PENDULUM TEST METHOD (Slider 96): Mean SRV:	39	P3
AS 4586:2013 (Amendment No. 1)	Slip resistance classification of new pedestrian surface materials, Appendix D: OIL-WET INCLINING PLATFORM TEST METHOD Corrected mean overall acceptance angle:	19°	R 11

In order to interpret the classifications, please refer to Standards Australia Handbook 198, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



REPORT NO: 8103.1
ISSUE DATE: 19 June 2018
MANUFACTURER: Kenbrock
PRODUCT DESC: Cushion Stone, Vinyl Tiles, PU Top Coat

PHOTOS:



Top view



Close up



REPORT NO: 8103.1
ISSUE DATE: 19 June 2018
MANUFACTURER: Kenbrock
PRODUCT DESC: Cushion Stone, Vinyl Tiles, PU Top Coat

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

WET PENDULUM TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS 4586:2013 (Appendix A)

Test Date: 6 June 2018

RESULTS: Location: Slip Resistance Laboratory Slider used: 96
Conditioned with grade P400 paper, dry
and Imperial Lapping Film Grade 3MIC, wet
Sample: Unfixed
Cleaning: Deionized water
Temperature: 22.1°C

Pendulum Friction Tester: ERM.030.001 (S/N: 0312, calibrated 16/06/2016)
Test conducted by: Khanh Ho

	Specimen				
	1	2	3	4	5
Last 3 swings (BPN)	41	39	40	43	39
	40	38	39	42	38
	40	38	38	42	38
Averages	40	38	39	42	38

Mean SRV : 39

CLASS :

P3



REPORT NO: 8103.1
ISSUE DATE: 19 June 2018
MANUFACTURER: Kenbrock
PRODUCT DESC: Cushion Stone, Vinyl Tiles, PU Top Coat

Page 4 of 5

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

OIL-WET INCLINING PLATFORM TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS 4586:2013 (Appendix D) (Amendment No. 1)

Test Date: 6 June 2018

Location: Slip Resistance Laboratory Test conducted by: KH, AG

Sample Unfixed

Joint width: 0 mm

Surface structure: Smooth
 Profiled
 Structured

RESULTS

Corrected mean overall acceptance angle: 19 °

Displacement space: not tested

CLASSIFICATION: Slip Resistance Assessment Group:

R 11

Displacement Space Assessment Group:

-

Test shoe used: Leipzig V73-SP



Infrastructure Technologies

Gate 5, 2 Normanby Road Clayton VIC 3168, Australia

Telephone: 61 3 9545 2777 Web: <http://www.csiro.au>

REPORT NO: 8103.1
ISSUE DATE: 19 June 2018
MANUFACTURER: Kenbrock
PRODUCT DESC: Cushion Stone, Vinyl Tiles, PU Top Coat

Page 5 of 5

Date and Place 19 June 2018, Clayton, Vic

Name, Title and Digital Signature:

A digital signature in black ink, appearing to be 'Khanh Ho', is overlaid on a semi-transparent grey circular background that contains the CSIRO logo.

KHANH HO
Technical Officer
Tel: 61 3 95452777
Email: Khanh.Ho@csiro.au