





Accredited for compliance with ISO/IEC 17025 Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

OIL-WET INCLINING PLATFORM SLIP RESISTANCE TEST

Kenbrock Springbrook

Prepared for: Gerflor Australasia Pty Ltd

Steven Gradecak 17 Cato Street

HAWTHORN EAST VIC 3123

Specimen Description: Kenbrock Springbrook, 183x1220 mm.

No. of Specimens: 3 off

Surface Structure: Smooth

Specimen Preparation: Washed with water and pH neutral detergent, rinsed then dried.

Specimen Configuration: Unfixed

Test Direction: Test conducted parallel with embossed finish.

Joint Type & Width: N/A
Air Temperature: 22°C

Test Standard: AS 4586:2013 Slip resistance classification of new pedestrian surface

materials, Appendix D - Oil Wet Inclining Platform Test

Test Shoe: Leipzig V73-SP

Test Location: ATTAR 44-48 Rocco Drive, Scoresby, VIC, 3179

Test Date: 8 December 2023

Test Personnel: Louie Karkatzoulis and Marcus Bosworth

Displacement Space	Not tested	
(rounded to the nearest 0.5cm³/dm²):		
Displacement Space Assessment Group	Not tested	
(Appendix E, AS 4586 - 2013):		
Corrected mean overall acceptance angle (α _{ave})	9°	
(rounded down to the nearest degree):	3	
Classification:	R9	

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip resistance be checked.

Prepared By:

Marcus Bosworth

Compliance and Testing Technician

Reviewed By:

Dale Siegle

Technical Consultant - Compliance Services

Approved Signatory






Figure 1: Kenbrock Springbrook
Arrow indicates direction of testing



CLASSIFICATION CRITERIA – AS 4586 - 2013 Oil Wet Inclining Platform Test – Appendix D

Compliance

TABLE 5: CLASSIFICATION OF PEDESTRIANSURFACE MATERIALS ACCORDING TO THE OIL-WET INCLINING PLATFORM TEST

Classification	Angle, degrees
No Classification	<6
R9	≥6 <10
R10	≥10 <19
R11	≥19 <27
R12	≥27 <35
R13	≥35