



# Infrastructure Technology

Manufacturing Flagship, Graham Road (PO Box 56), Highett, Victoria, Australia 3190  
Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: tiles@csiro.au Web: <http://www.cmse.csiro.au>

Registered Testing Authority - CSIRO

11 December 2014

Our Ref. EN13 / 415 03/0212

## TEST REPORT No. 7233.2s

Requested by: Gerflor Australasia P/L  
17 Cato St  
Hawthorn East  
VIC 3123  
on (date): 1 December 2014  
Manufacturer: Gerflor Australasia  
Product Desc.: Texline

Sampling details:  
Where: Delivered  
Date: 1 December 2014  
By whom: Courier  
How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 3 pages

### SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

	Result	Class
AS 4586:2013	Slip resistance classification of new pedestrian surface materials, Appendix D: OIL-WET Ramp Corrected mean overall acceptance angle: 12° (* ) = AS 4568:2004 classification	R 10

In order to interpret the classifications, please refer to Standards Australia Handbook 198, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



REPORT NO: 7233.2s  
ISSUE DATE: 11 December 2014  
MANUFACTURER: Gerflor Australasia  
PRODUCT DESC: Texline

Page 2 of 3

**SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS**

**OIL-WET RAMP TEST METHOD**

TEST CARRIED OUT IN ACCORDANCE WITH  
AS 4586:2013 (Appendix D)

Test Date: 5 December 2014

Location: Slip Resistance Laboratory Test conducted by: KH, AG

Sample Fixed

Joint width: 0 mm

Surface structure:  Smooth  
 Profiled  
 Structured

**RESULTS**

Corrected mean overall acceptance angle: 12 °

Displacement space: not tested

**CLASSIFICATION:**

**Slip Resistance Assessment Group:**

**R 10**

**Displacement Space Assessment Group:**

**-**

Test shoe used: Uvex Athletic



## Infrastructure Technology

Manufacturing Flagship, Graham Road (PO Box 56), Highett, Victoria, Australia 3190

Telephone: 61 3 9252 6000 Facsimile: 61 3 9252 6244 Email: [tiles@csiro.au](mailto:tiles@csiro.au) Web: <http://www.cmse.csiro.au>

---

REPORT NO: 7233.2s  
ISSUE DATE: 11 December 2014  
MANUFACTURER: Gerflor Australasia  
TILE DESC: Texline

Page 3 of 3

---

Date and Place 11 December 2014, Highett, Vic

Name, Title and Digital Signature:

A digital signature in black ink, appearing as a stylized cursive 'KH' followed by a horizontal line, overlaid on a faint, circular CSIRO logo watermark.

**KHANH HO**  
**Technical Officer**  
Tel: 61 3 92526119  
Fax: 61 3 92526244  
Email: [Khanh.Ho@csiro.au](mailto:Khanh.Ho@csiro.au)

---